

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

PRELIMINARY AN		1999 1999	أمدامك
OF SAID SUSPENSION			ECEIV
OF PREPARATION AND UTILISATION)	3 5	
PRECIPITATION SILICA, METHODS)	است ماد	70
For: CONCENTRATED SUSPENSION)	ქ 2	
Filed: January 7, 1997)		
Application No.: CPA of 08/765,901) Examiner: S. Hendrickso	n	
Evelyne PRAT et al) Group Art Unit: 1754		
n re Patent Application of)		

Assistant Commissioner for Patents Washington, D.C. 20231

Sir:

Prior to examination on the merits, please amend the above-identified application as follows:

IN THE CLAIMS:

Kindly amend claim 39 as follows:

39. (Three times amended) A method for the preparation of an aqueous suspension of precipitated silica, having solids content of between 10 and 40% by weight, which viscosity is lower than $4x10^{-2}$ Pa.s at a shear rate of 50 s⁻¹ and wherein the amount of silica present in the supernatant obtained after centrifuging the said suspension at 7500 revolutions per minute for 30 minutes represents more than 50 % of the weight of the silica present in the suspension, comprising the steps of :